



技術資料表 Technical Data Sheet

BGNTYPE

高剛性強化、耐熱、熱安定，高耐衝，低浮纖，高黑度，流動性佳
High rigidity reinforcement, heat resistance, thermal stability,
high impact resistance, low floating fiber, high blackness,
good fluidity

樹脂 Resin PC Polycarbonate

規格 Grade BG56-N1 BK

來源 source 上禾伸企業

描述 Description

■添加 30%GF 高剛性強化，耐熱 144°C，高溫成型加工相對穩定。

Added 30% GF for high rigidity reinforcement, heat resistance of 144°C, and relatively stable high-temperature molding processing.

■PC 塑料與 GF 高結合相容，物性有一定水準之上，高耐衝、高流動，低浮纖。

PC plastic is highly compatible with GF, and its physical properties are above a certain level, with high impact resistance, high flow, and low floating fibers.

■此規格有添加相容劑，可提高相容極性，塑料產品射出後，再加工附著、黏著、包覆，結合度會提高許多。

This specification has a compatibilizer added to improve the polarity of the compatibility. After the plastic product is injected, it will be processed for attachment, adhesion, and coating, and the degree of bonding will be much improved.

成型模式 射出成型

Forming mode Injection Molding

特性 Properties

項目 Project	單位 Unit	測試標準 Testing standards	標準數值 Typical Value
填充劑含量 Filler Content	%		30
比重 Specific Gravity	g/cm ³	ASTM D792	1.41
流動指數 MFR,(MI) 300×2.16KG	g/10min	ASTM D1238	25
收縮率-平行 Mold Shrinkage MD	%	3 mm t	0.1
收縮率-垂直 ⊥ Mold Shrinkage TD			~0.4
耐燃性 Flammability		UL-94	V1
顏色 Color			natural color

PC BG56-N1 BK TDS 1/2



機械特性 Mechanical properties

伸張降伏強度 Tensile Strength at Yield			1250
伸張斷裂強度 Tensile Strength at Break	kg/ cm ²	ASTM D638	950
拉伸模數 Tensile Modulus			45500
斷裂伸張率 Tensile Elongation at Break	%		3.3
彎曲強度 Flexural Strength	kg/ cm ²	ASTM D790	1950
彎曲模數 Flexural Modulus			78500
衝擊強度(缺口式)IZOD Impact (notched)	23°C kg-cm/cm	ASTM D256	18.0
硬度 Rockwell/Shore Hardness	D	ASTM D785/D2240	80

熱力特性 Heat properties

熱變型溫度 18.54kg/ cm ² H D T	°C	ASTM D648	144
--------------------------------------	----	-----------	-----

電氣特性 Electrical properties

體積固有阻抗 Volume inherent impedance	Ω-cm	ASTM D257	10 ¹⁴
表面阻抗 Surface resistivity	Ω		10 ¹⁴

成型條件 Molding conditions

烘乾溫度 Drying temp. °C	100	烘乾時間 Drying time H	4
進料區溫度 Feed zone temp. °C	265~295	壓縮區溫度 Compression zone temp. °C	275~300
計量區溫度 Metering zone temp. °C	285~300	噴嘴溫度 Nozzle temp. °C	285~300
模具溫度 Mold temp. °C	100	射出壓力 Injection pressure Kg/ cm ²	900~1600

*雖然上述信息是出於善意並被認為是準確的，但我們不保證依賴此類信息取得令人滿意的結果，並且不承擔因使用此類信息而引起的任何損失或損害的全部責任。*以上數值係僅供選擇用途品級之參考。

Although the above information is made in good faith and is believed to be accurate, we do not guarantee reliance on such information to obtain satisfactory results, and we do not assume full responsibility for any loss or damage caused by the use of such information. The above values are for reference only for the selected grade.