

技術資料表 Technical Data Sheet

WACTYPE

添加 CNT 奈米碳管永久抗靜電、靜電消散，低導電，阻燃
Add CNT nanotubes for permanent anti-static, static
dissipation, low conductivity, flame retardant

樹脂 Resin	PESU Polyether sulfone
規格 Grade	WANC51-A2 BK
來源 source	上禾伸企業

描述 Description

■添加 CNT 奈米碳管，永久抗靜電、靜電消散，低導電。

Add 10% inorganic carbon fiber to enhance rigidity, permanently antistatic, static dissipative, and low conductivity.

■熱變形溫度達 205°C，高 TG 點 220°C，且可持續在高溫 170~180°C 環境中使用，長期使用耐熱溫度高。

The heat deformation temperature reaches 205°C, the highest TG point is 220°C, and it can be used continuously in a high temperature environment of 170~180°C, with high heat resistance for long-term use.

■剛性好、機械强度高，尺寸高度穩定。

Good rigidity, high mechanical strength and highly stable dimensions.

■優異的耐水解性，與良好的耐化學性，抗藥性佳，耐強鹼性佳。

Excellent hydrolysis resistance, good chemical resistance, good drug resistance, and good alkali resistance.

■極佳的阻燃性能，具有自熄性，在不添加阻燃劑的情況下可實現高達 UL94 V-0 級的阻燃性。

Excellent flame retardant performance, self-extinguishing, and can achieve flame retardancy up to UL94 V-0 without adding flame retardants.

成型模式	射出成型
Forming mode	Injection Molding

特性 Properties

填充劑含量 Filler Content	%		10
比重 Specific Gravity	g/cm ³	ASTM D792	1.39
流動指數 MFR, (MI) 380×2.16KG	g/10min	ASTM D1238	15
收縮率-平行 Mold Shrinkage MD			0.2
收縮率-垂直 ⊥ Mold Shrinkage TD	%	3 mm t	~0.5
耐燃性 Flammability		UL-94	V0 1.5mm
顏色 Color			Black

機械特性 Mechanical properties

伸張強度 Tensile Strength	kg/ cm ²	ASTM D638	950
斷裂伸張率 Tensile Elongation at Break	%		4.5
彎曲強度 Flexural Strength	kg/ cm ²	ASTM D790	1300
彎曲模數 Flexural Modulus			30000
衝擊強度(缺口式) IZOD Impact (notched)	23°C -40°C	kg-cm/cm	ASTM D256
			5.0 **

熱力特性 Heat properties

熱變型溫度 18.54kg/ cm ² H D T	°C	ASTM D648	205
--------------------------------------	----	-----------	-----

電氣特性 Electrical properties

體積固有阻抗 Volume inherent impedance	ASTM D257	Ω·cm	10 ⁻⁶
表面阻抗 Surface resistivity		Ω	10 ⁻⁶

成型條件 Molding conditions

烘乾溫度 Drying temp. °C	150	烘乾時間 Drying time H	6
進料區溫度 Feed zone temp. °C	345~365	壓縮區溫度 Compression zone temp. °C	345~365
計量區溫度 Metering zone temp. °C	350~370	噴嘴溫度 Nozzle temp. °C	355~375
模具溫度 Mold temp. °C	135~170	射出壓力 Injection pressure Kg/ cm ²	700~1100

*雖然上述信息是出於善意並被認為是準確的，但我們不保證依賴此類信息取得令人滿意的結果，並且不承擔因使用此類信息而引起的任何損失或損害的全部責任。*以上數值係僅供選擇用途品級之參考。

Although the above information is made in good faith and is believed to be accurate, we do not guarantee reliance on such information to obtain satisfactory results, and we do not assume full responsibility for any loss or damage caused by the use of such information. The above values are for reference only for the selected grade.